



## **UPM Raflatac Technical Information**

05-08-2020 EN SI

Product PP CLEAR TC 50 P / RP37 / WHITE GLASSINE 65-FSC

Sales Code 9D/RP37/GZI EAN 6415788353707

Product use Product designed for labelling in applications where resistance against water, oil and chemicals

is important. it suits general applications in Food, HPC & Beverage.

Typical technical values

Face PP CLEAR TC 50

Product Transparent, glossy, biaxially oriented, both sides coated polypropylene film.

Substance 47 g/m² ISO 536 Caliper 51 μm ISO 534

Printability Flexography, screen, letterpress and offset. Special inks designed for non-absorbent materials

should be used. Thermal transfer printing with selected ribbons.

Adhesive RP37

Type Permanent

Composition Waterborne acrylic

Tack 10 N/25mm FTM 9

Labelling temperature min 5 °C
Service temperature min -20 °C
Service temperature max 80 °C

Backing WHITE GLASSINE 65-FSC

Product White glassine, transparent backing paper

Substance 58 g/m² ISO 536 Caliper 51 μm ISO 534

Sustainability The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate

SGSCHCOC-004879.

**Performance** 

Total caliper 122 µm

 $Shelf\ life \qquad \qquad From\ date\ of\ manufacture:\ 24\ months,\ under\ FINAT\ defined\ storage\ conditions\ (+20-25\,^{\circ}C\ and\ and\ before\ the conditions\ (+20-25\,^{\circ}C\ and\ before\ the conditions\$ 

40-50% RH). Prolonged storage at higher temperatures and/or humidity levels will shorten the

shelf life.





Disclaimer

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

